

## **COATING UV7150 Flexo Gloss Primer FCM**

Galaxy Coating UV7150 is a very fast radical curing gloss UV primer. The coating is suitable for priming of metallized substrates to improve adhesion of subsequently applied UV inks. The coating is for use in combination with a coating unit. Formulated for food packaging according EC 1935/2004, when migration testing is carried out by the end user. Compliant with Nestlé list 10-2018, Swiss Ordinance for Food Packaging and EuPIA recommendations. Does not contain Bisphenol A or raw materials derived from Bisphenol A.

**Application:** Recommended coating weight 2 – 4 grms/m2 (wet)

Suitable for aluminium foils, PE and PP. Tests recommended.

Suitable for flexo anilox or roller coater coating unit.

**Use:** Use solvent and alkali resistant inks

Press ready

Optimal properties obtained 24hrs after printing

4

1

Suitable for use in food packaging industry, sensitive packaging applications, appropriate migration tests are recommended for full

suitability

**Performance key:** Gloss 8 1 matt – 10 highest gloss

Cure speed

Slip

Rub resistance 4

Block resistance 5

Glueability 5 Specific films to be tested

Solvent resistance 4 Specific conditions to be tested

\*\* 1 (Slow / Low) – 5 (Fast / High) \*\*

**Typical constants:** Viscosity 60 – 80 sec DIN4 @ 25°

Specific gravity  $1.10 \text{ g/cm}^3 \pm 0.05$ 

Apearance Brownish, hazy liquid

**Storage conditions:** Store away from excessive heat, out of direct sunlight and in closed

packaging. Prefered conditions between 15 - 20°C

Cleaning: Use a proper UV-wash, UV-Wash UV4000-IQ-S

**Shelf life:** In unopened, original packaging, 8 months from manufacturing date





Version: 01-2012

The information provided in this technical data sheet is to inform our customers. A successful application depends on a variety of different factors. Therefore the advice given in this technical data sheet cannot be used as basis for claims. Our recommendation is where possible to perform tests before entering production runs.

