

TECHNICAL DATA SHEET

UV FLEXO VARNISHES

DESCRIPTION Universal UV flexo varnish range suitable for general label printing.

- PROPERTIES**
- ✓ Excellent adhesion properties
 - ✓ Fast cure
 - ✓ Excellent printability
 - ✓ Excellent chemical resistance

RANGE

| Product | Code |
|--|-------|
| UV FLEXO GLOSS VARNISH | |
| Foil Blockable Gloss Varnish | EL158 |
| Gloss Varnish | EL180 |
| High Rub/Slip Gloss Varnish | EL056 |
| High Rub/Slip Gloss Varnish OB | EL059 |
| Shrink Sleeve Gloss Varnish | EL221 |
| High Slip Foil Blockable Gloss Varnish | EL459 |
| UV FLEXO SATIN VARNISHES | |
| Foil Blockable Satin Varnish | EL370 |
| High Slip Satin Varnish | EL366 |
| UV FLEXO MATT VARNISHES | |
| Foil Blockable Matt Varnish | EL371 |
| Foil Blockable Ultra Matt Varnish | EL372 |
| Foil Blockable High Rub Matt Varnish | EL400 |
| High Slip Matt Varnish | EL367 |
| Shrink Sleeve Matt Varnish | EL254 |

SUBSTRATES Suitable for a wide range of coated papers, films and label stocks including:

- ✓ Coated PE, PP, PVC, PET, and OPP
- ✓ Shrink films, typically* PVC, PET, PET-G, OPS (EL221 & EL254)

* Due to the diverse nature of shrink films it is essential that each grade/application is tested thoroughly prior to commercial production

The suitability of uncoated synthetic substrates such as PP should be tested before printing. The surface tension should be 38 dyne/cm or above. Corona treatment should be considered to improve the wetting and adhesion onto the substrate.

APPLICATION**Mix well before use.****Anilox Selection:**120-200 l/cm (300-500 lpi) volume 3-8 cm³/m²**Minimum lamp power – 160 W/cm**

Fully cured UV flexo varnishes will obtain resistance properties 24 hours after printing. Foil blockable varnishes are not suitable for direct thermal overprinting. Please be aware that the over curing of a product may lead to problems with thermal transfer overprinting.

Clean equipment immediately after use.

These products are not intended for food packaging applications.

STORAGE & HANDLING

Containers should be tightly closed immediately after use. All products, including uncontaminated press returns and unopened containers, should be stored at temperatures between 5°C and 25°C.

Shelf life is 12 months from date of manufacture (as indicated on the label).

HEALTH & SAFETY

Please refer to relevant SDS for information on labelling classifications, waste product and container disposal, and personal protection measures.

AUXILIARY PRODUCTS

Cleaner: RLA350 UV Wash

FURTHER INFORMATION

For more information, please contact your local representative or email technical@pulserl.com.

DISCLAIMER

The information contained in this data sheet is correct to the best of our knowledge. It is intended as a guide only for the optimum use of the named product(s) and is not intended as a warranty or as a specification. The product(s) included in this datasheet may not be suitable for use with other materials or in processes other than those specifically described. The user(s) should always make their own tests to establish that the product(s) meets their specification and complies with any appropriate guidelines or regulatory requirements.