
TECHNICAL DATA SHEET

20-803 GLASSINE BACKING BLACK

DESCRIPTION UV flexo glassine backing black ink suitable for general label printing.

PROPERTIES

- ✓ High colour strength
- ✓ Excellent adhesion properties
- ✓ Printing speeds of 50-150 m/min (dependent on UV lamp power)
- ✓ Fast cure
- ✓ Excellent printability

SUBSTRATES Suitable for a wide range of coated papers, films and label stocks. Specifically formulated for barcoding and text work on the back of glassine.

The suitability of uncoated synthetic substrates such as PP should be tested before printing. The surface tension should be 38 dyne/cm or above. Corona treatment should be considered to improve the wetting and adhesion onto the substrate.

APPLICATION **Mix well before use.**

Anilox Selection:
120-180 l/cm (300-450 lpi) volume 3-6 cm³/m²

Minimum lamp power – 160 W/cm

Fully cured UV flexo inks will obtain resistance properties 24 hours after printing.

Clean equipment immediately after use.

This product is not intended for food packaging applications.

STORAGE & HANDLING Containers should be tightly closed immediately after use. All products, including uncontaminated press returns and unopened containers, should be stored at temperatures between 5°C and 25°C.

Shelf life is 12 months from date of manufacture (as indicated on the label).

HEALTH & SAFETY Please refer to relevant SDS for information on labelling classifications, waste product and container disposal, and personal protection measures.

**AUXILIARY
PRODUCTS**

Cleaner: RLA350 UV Wash

**FURTHER
INFORMATION**

For more information, please contact your local representative or email technical@pulserl.com.

DISCLAIMER

The information contained in this data sheet is correct to the best of our knowledge. It is intended as a guide only for the optimum use of the named product(s) and is not intended as a warranty or as a specification. The product(s) included in this datasheet may not be suitable for use with other materials or in processes other than those specifically described. The user(s) should always make their own tests to establish that the product(s) meets their specification and complies with any appropriate guidelines or regulatory requirements.